(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 1 July 2004 (01.07.2004)

PCT

(10) International Publication Number WO 2004/055091 A1

- (51) International Patent Classification⁷: C08G 18/67, C08K 5/526, C03C 25/10, C09D 4/06, 175/16
- (21) International Application Number:

PCT/NL2003/000887

(22) International Filing Date:

12 December 2003 (12.12.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

JP2002-363908 16 December 2002 (16.12.2002) JP JP2003-295025 19 August 2003 (19.08.2003) JP

- (71) Applicant (for all designated States except US): DSM IP ASSETS B.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): YAMAMOTO, Keiichi [JP/JP]; 2-13-28-303 Kawaguchi, Tsuchiura, Ibaraki 300-0033 (JP). KOMIYA, Zen [JP/JP]; 2-18-33 MI-3 Umezono, Tsukuba Ibaraki 305-0045 (JP).

- (74) Agent: RENKEMA, J.; DSM Intellectual Property, P.O. Box 9, NL-6160 MA Geleen (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



(57) Abstract: A radiation-curable resin composition comprising (A) 0.1-10 wt% of a compound including a phosphite group and a phenolic hydroxyl group was found to have excellent storage stability, produces a cured product which excels in durability and generates only a small amount of hydrogen gas, and is useful for coating optical fiber.